



# TECHNICAL DATA - GL.01

<b>PHOTOVOLTAIC GLASS</b>		<b>579 x 2524</b>
		<b>XL Vision (30%)</b>
<b>Electrical data test conditions (STC)</b>		
Nominal peak power	41	P <sub>mpp</sub> (Wp)
Open-circuit voltage	197	V <sub>oc</sub> (V)
Short-circuit current	0,36	I <sub>sc</sub> (A)
Voltage at nominal power	135	V <sub>mpp</sub> (V)
Current at nominal power	0,30	I <sub>mpp</sub> (A)
Power tolerance not to exceed	±5	%
STC: 1000 w/m <sup>2</sup> , AM 1.5 and a cell temperature of 25°C, stabilized module state.		
<b>Mechanical description</b>		
Length	579	mm
Width	2524	mm
Thickness	60,24	mm
Surface area	1,46	sqm
Weight	92	Kgs
Cell type	α-Si	Thin Film
Transparency degree	XL	Vision (30%)
Front Glass	6 mm	Tempered Glass
PV Active Glass	3,2 mm	Float Glass
Rear Glass	6 mm	Tempered Glass
Air Chamber	16 mm	Argon Chamber
Inner Glass	4 mm	Tempered Glass Low-e
Air Chamber	16 mm	Argon Chamber
Inner Glass	6 mm	Tempered Glass Low-e
Thickness encapsulation	1,52 mm	PVB Foils (x2)
Category / Color code		
<b>Junction Box</b>		
Protection	IP65	
Wiring Section	2,5 mm <sup>2</sup> or 4,0 mm <sup>2</sup>	
<b>Limits</b>		
Maximum system voltage	1000	V <sub>sys</sub> (V)
Operating module temperature	-40...+85	°C
Max. Series Fuse	3	A
<b>Temperature Coefficients</b>		
Temperature Coefficient of P <sub>mpp</sub>	-0,19	%/°C
Temperature Coefficient of V <sub>oc</sub>	-0,28	%/°C
Temperature Coefficient of I <sub>sc</sub>	+0,09	%/°C



\* All technical specifications are subject to change without notice by Onyx Solar **global leader in building integrated photovoltaic glass**



SPAIN (Avila)  
 C/ Rio Cea 1, 46 • 05004  
 Phone: +34 920 21 00 50  
 info@onyxsolar.com • www.onyxsolar.es

UNITED STATES (New York)  
 79 Madison Avenue Suite 640 • NY 10016  
 Phone: +1 917 261 4783  
 usa@onyxsolar.com • www.onyxsolar.com